

Cempatch MH

One component high build high strength cementitious repair mortar



Description

Cempatch MH is a one component polymer modified and fibre reinforced dimensionally stable repair mortar. Cempatch MH is a blend of dry powders, acrylic polymer, selected aggregates and fibres which when mixed with water produces a thixotropic mortar suitable for vertical and overhead application.

Applications

- ▲ Repair of all types of structural concrete where high strength and extremely low shrinkage properties are required.
- ▲ For the repair of vertical and overhead elements.
- ▲ As a repair mortar for all structural elements in buildings, water retaining structures, industrial plants, bridges, etc.

Advantages

- ▲ Shrinkage controlled polymer modified cementitious repair mortar.
- ▲ Easy to apply, single component, requires only addition of water.
- ▲ Extremely low permeability to water, providing excellent protection to steel reinforcements and host concrete.
- ▲ Thixotropic properties allowing extra high build for vertical and overhead applications.
- ▲ Suitable for internal and external application.
- ▲ Water vapour permeable.
- ▲ Cost effective, hand applied no formwork is required.

Standards

Cempatch MH complies with ASTM C109/109M-02, DIN1048, Part 5, ASTM C157-93 & BS1881, Part 121.

Method of Use

Substrate Preparation

All damaged and weak concrete should be cut back to reach sound concrete and/or to a minimum depth of at least 10 mm.

Corroded steel reinforcement should be grit blasted to remove all rust traces. In case of significant loss in the steel reinforcement cross section, the steel should be replaced.

Technical Properties:

Compressive strength:	> 60 MPa @ 7 days
ASTM C109/109M-02	> 75 MPa @ 28 days
Water penetration:	< 5 mm
DIN 1048, Part 5	
Colour:	Grey
Drying shrinkage:	< 300 microstrain @ 7 days
ASTM C157 - 93	< 550 microstrain @ 28 days
Rapid chloride permeability:	< 500 Coulombs
AASHTO 277-93	
Tensile strength:	> 6 MPa @ 28 days
ASTM C190	
Flexural strength:	> 13 MPa @ 28 days
ASTM C348	
Mixing ratio:	3.25 litre of water for 25 kg bag of Cempatch MH
Fresh wet density:	2.2 ± 0.1 g/cm ³
Minimum application temperature:	5°C
Water absorption:	< 2%
BS 1881, Part 121	

Remove all concrete form around exposed steel reinforcements by 10 mm thickness.

The perimeters of the repair area should be saw cut to a minimum depth of 10 mm. The prepared area should be cleaned thoroughly by brush and/or compressed air.

Priming

All grit blasted steel reinforcements should be primed within 2 - 4 hours with one or two coats of zinc rich epoxy coating Repcoat ZR.

Areas to be repaired with Cempatch MH should be soaked with clean water before applying the repair mortar. All excess water should be removed prior to applying Cempatch MH.

Cempatch MH

Mixing

To ensure proper mixing, a mechanically powered mixer or drill fitted with suitable paddle should be used. 3.25 litre of clean water should be added to clean container.

The powder is then added slowly to the water while mixing continuously with low speed mixer/drill (400 - 600 rpm). Mixing time should be continued for 3 minutes until uniform consistency is obtained.

Please note that adding more water will result in lower physical properties.

Placing and Finishing

Cempatch MH can be applied by trowel or hand. The mixed mortar should be applied using firm pressure to fully compact the mortar to ensure good adhesion with the steel reinforcements and the substrate. Finishing and leveling should be carried out initially by wooden or plastic float. Final finishing should be carried out using steel float.

Curing

As Cempatch MH is a cementitious based material, it should be cured in a similar method to concrete. Curing can be conducted by using Setseal A or by wet hessian sheets covered with polyethylene sheets.

Cleaning

All tools should be cleaned immediately after application using fresh water. Hardened materials must be cleaned mechanically.

Packaging

Cempatch MH is available in 25 kg bags.

Thicknesses and Size Limitations

Cempatch MH can be applied in a single application for sections up to 50 mm thick in overhead applications and 75 mm thick in vertical applications. Thickness should not be less than 10 mm deep in all applications.

Cempatch MH repair area should not exceed 2.5 m² in single application. For horizontal and small pocket applications, thickness can be up to 100 mm.

Yield

Approximately 12.5 - 13.5 litre per 25 kg bag. (77 bags/ m³).

Storage

Cempatch MH has a shelf life of 12 months if stored at temperatures between 2°C and 50°C in original unopened bags.

If these conditions are exceeded, DCP Technical Department should be contacted for advise.

Cautions

Health and Safety

Cempatch MH may cause irritation to skin or eyes. In case of accidental contact with eyes, immediately flush with plenty of water for at least 10 minutes and seek medical advise if necessary.

For further information refer to the Material Safety Data Sheet.

Fire

Cempatch MH is nonflammable.

More from Don Construction Products

A wide range of construction chemical products are manufactured by DCP which include:

- ▲ Concrete admixtures.
- ▲ Surface treatments
- ▲ Grouts and anchors.
- ▲ Concrete repair.
- ▲ Flooring systems.
- ▲ Protective coatings.
- ▲ Sealants.
- ▲ Waterproofing.
- ▲ Adhesives.
- ▲ Tile adhesives and grouts.
- ▲ Building products.
- ▲ Structural strengthening.

Note:

We endeavour to ensure that any information, advice or recommendation we may give in product literature is accurate and correct. However, because we have no control over where and how products are applied, we cannot accept any liability arising from the use of the products.